

Features

- · Good thermal conductivity
- · Heat curing
- · A:B = 1:1; Easy to mix
- · Can be applied with pistol & Easy to assemble
- · Low viscosity

Applications

REACH Compliant

S730

Electronic components - Electric Vehicles, 5G, Autopilot System, Mobile Phone, AIOT, HPC (High Performance Computing), Server, IC, CPU, MOS, LED, Mother Board, Power Supply, Heat Sink, LCD-TV, Notebook, PC, Telecom Device, Wireless Hub, DDR II Module, etc.

Global

Storage

Epoxy Potting Compound has a shelf-life of twelve (12) months from the date of manufacture, as indicated by the lot number, when stored in the original, unopened contained at or below 25° C.

Operation Manual





2 Put the tube in.



Silicone Potting Compound

RoHS Compliant

1 Push the latch and insert the stick.

Properties

Mixing Ratio

Hardness: 17 (Shore A)

0 0.8 1.2 1.4 1.6 1.7 1.8 2.2 3.2 3.6 4.0 4.5 5	.0 15 20 0	5 10 1	15 20 25	30 40 80
Droportion	\$730	Unit	Toloranco	Test Method
Properties	3730		Tolerance	Test Method
Thermal Conductivity	2.1	W/mK	±10%	ASTM D5470
Color	Gray	-	-	Visual
Dielectric Breakdown Voltage	12.2	KV/mm	±10%	ASTM D149
Volume Resistance	>1013	Ohm-m	-	ASTM D257
Density	2.5	g/cm ³	±10%	ASTM D792
Working Temperature	-50~+200	°C	-	-
Viscosity	<50000	cps	-	ASTM D2393
Curing Time @25° C	300	Min	-	-
Curing Time @60° C	30	Min	-	-
Curing Time @100° C	5	Min	-	-
Standard Format	100g/1kg	Tube/Pot	-	-
Hardness	17	Shore A	±2	ASTM D2240

Component A is a mixed material of epoxy and thermal conductive powder. It is normal to cause precipitation and stratification due to different density. Before use, please use a flat spatula or other stainless tools to evenly mix component A to achieve the best thermal conductivity.

1:1

T-Global Techonology Co., Ltd

Version17 20200501

gram

T-Global Technology are proud to announce the launch of a new company logo and mission statement as part of the ongoing growth and volution of our company's brand.

No.33, Ln.50, Daren Rd., Taoyuan Dist., Taoyuan City 330058, Taiwan

Thermal Conductivity: 2.1 W/mK

T +886-3-361-8899 E service@tglobal.com.tw W www.tglobalcorp.com

NOTICE: The information contained herein is to the best of our knowledge true and accurate. Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. All specifications are subject to change without notice. The protective film does not affect the function of the product. If there is no special requirement, the default depends on T-Global.Since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology's invoice, quotation, or order acknowledgment.

We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.